

UNITED STATES PATENT APPLICATION

OF

MICHAEL B. KORZENSKI

CHONGYING XU

THOMAS H. BAUM

DAVID MINSEK

ELIODOR G. GHENCIU

FOR

**COMPOSITIONS AND METHODS FOR HIGH-EFFICIENCY CLEANING OF
SEMICONDUCTOR WAFERS**

EXPRESS MAIL CERTIFICATE OF MAILING

Express Mail Label Number: EV178872462US
Date of Deposit: June 24, 2003

COMPOSITIONS AND METHODS FOR HIGH-EFFICIENCY CLEANING/POLISHING OF SEMICONDUCTOR WAFERS

FIELD OF THE INVENTION

[0001] The present invention relates to compositions and methods for high-efficiency cleaning of semiconductor wafers.

[0002] DESCRIPTION OF THE RELATED ART

[0003] The fabrication of multi-layer semiconductor circuits requires the deposition of multiple patterned layers of semiconductor, conductor and dielectric materials. Patterning is conventionally carried out by optical imaging of a photoresist layer formed from a composition containing a soluble polymer and a photoactive compound. Following patterning, deposition, and etching, the photoresist layer must be completely removed before the next processing step.

[0004] Plasma ashing can remove photoresist but leaves a post-ash residue on the substrate that must be removed. Typically, liquid photoresist or post-ash residue removers are employed. Such removers, however, generate a large amount of hazardous waste that is harmful to the environment, and costly to dispose of, or treat.

[0005] The art therefore has a continuing and critical need for improved compositions for cleaning of residues, e.g., post-ashing residues, from semiconductor wafers (such term herein including wafer base or substrate articles per se, as well as such articles having material deposited thereon or therein to form semiconductor devices or precursor structures for such devices.

[0006] As a further and specific problem attendant the use of conventional liquid-based cleaning and post-etch residue removal compositions, the geometric scale of features in semiconductor device architectures continues to diminish. At critical dimensions (of high aspect ratio vias, deep trenches and other semiconductor device or precursor structure features)

below 0.1 μm , the high surface tension that is characteristic of aqueous compositions used to clean wafers prevents the penetration of the composition into the semiconductor wafer features.

[0007] Thus, although liquid-based cleaning and post-etch residue removal integrated circuit processes are well-developed and accepted for device manufacturing, their future utility is highly questionable. Apart from problems attendant the high surface tension of aqueous cleaning compositions, copper, porous, low-k multi-layers may require special, non-aqueous cleaning to eliminate aqueous contamination of the pores and consequent reduction of device yields when pore contaminants cannot be removed. Additionally, the dielectric constant of low k materials is critical and aqueous contamination can negatively increase the dielectric constant.

[0008] The foregoing highlights the need of the art for improved cleaning compositions and methods for removal of post-etch lithographic resist (polymer) residue, removal of chemical mechanical planarization (CMP) particles in deep-trench, high aspect ratio vias, removal of metal oxides, metal residues and metal contaminants that remain on the wafer after etching, CMP and interconnect processes (e.g., physical vapor deposition (PVD), chemical vapor deposition (CVD) and plating) for metalization.

[0009] SUMMARY OF THE INVENTION

[0010] The present invention relates to compositions and methods for high-efficiency cleaning of semiconductor wafers.

[0011] In one aspect, the invention relates to a composition for cleaning semiconductor wafers, wherein the composition includes a supercritical fluid and at least one additive selected from the group consisting of:

- a. fluoro-species; and
- b. primary and/or secondary amine(s).

[0012] Another aspect of the invention relates to a method of cleaning of a semiconductor wafer, wherein the method comprises contacting the semiconductor wafer with a supercritical fluid-based cleaning composition including supercritical fluid and at least one additive selected from the group consisting of:

- a. fluoro-species; and
- b. primary and/or secondary amine(s).

[0013] Other aspects, features and embodiments of the invention will be more fully apparent from the ensuing disclosure and appended claims.

[0014] BRIEF DESCRIPTION OF THE DRAWINGS

[0015] FIG. 1 is a scanning electron microscope (SEM) micrograph of a post-ashing trench structure in a two-layer coating on a silicon substrate, wherein the two-layer coating includes a first (lower) layer of low k dielectric material and a second (upper) layer of a capping dielectric material, before cleaning.

[0016] FIG. 2 is an SEM micrograph of the trench structure of FIG. 1, after washing with a cleaning composition comprising SCCO_2 , ethanol, $(\text{C}_2\text{H}_5)_3\text{N}(3\text{HF})$ and boric acid.

[0017] FIGS. 3A and 3B are scanning electron microscope (SEM) micrographs of a post-ashing trench structure in a two-layer coating on a silicon substrate, wherein the two-layer coating includes a first (lower) layer of low k dielectric material and a second (upper) layer of a capping dielectric material, before cleaning.

[0018] FIG. 4 is an SEM micrograph of the trench structure of FIG. 1, after washing with a cleaning composition comprising SCCO_2 , isopropanol, NH_4F and non-ionic surfactant.

[0019] DETAILED DESCRIPTION OF THE INVENTION, AND PREFERRED EMBODIMENTS THEREOF

[0020] The present invention relates to compositions and methods for high-efficiency cleaning of semiconductor wafers. The compositions include supercritical fluid and at least one additive selected from the group consisting of (I) fluoro-species and (II) primary and/or secondary amine(s). Such compositions optionally further include co-solvent, low k material- attack-inhibitor, and/or surfactant species, as variously employed in specific embodiments of the invention.

[0021] In general, the compositions of the invention as variously hereinafter described may alternatively "comprise," "consist" or "consist essentially of" the ingredients specified for such compositions. Additionally, compositions of the invention can further include stabilizers, dispersants, etc., and other ingredients, as appropriate to the formulation and use of such compositions.

[0022] In one aspect, the invention provides wafer-cleaning compositions utilizing a supercritical fluid (SCF) in combination with hydrogen fluoride and/or a fluoride ion source.

[0023] The invention in such aspect utilizes a supercritical fluid component having the viscosity and diffusivity of a gas, and thereby capable of penetrating quickly into interstices, trenches, high aspect ratio vias, and other finely-dimensioned features of the wafer article. The supercritical fluid comprises a substantial major fraction of the cleaning composition. The cleaning composition also compensates for the polarity of the SCF by inclusion of a component having a polarity that is opposite to that of the SCF. For example, the non-polar character of a SCCO_2 component is compensated by incorporation of a hydrogen fluoride (HF) and/or fluoride ion

[0024] (F) component, hereafter referred to as "fluoro species," so that the SCF's inherently low ability to solubilize polymer and/or post-ash residues is obviated by the presence of the fluoro species, which imparts to the composition the capability to solubilize polar surface residues on the semiconductor wafer, and to increase the etch rates of aqueous as well as non-aqueous solutions.

[0025] It is indeed surprising that SCF and fluoro species in combination would be an effective cleaning combination for photoresist and post-ashing residues on the semiconductor wafer, since fluoro species exhibit very low solubilities in SCF media, and since it would be expected that the SCF would be such an effective penetrant as to blanket the wafer surface preferentially and produce only a low level, if any, of polymer and/or post-ashing residue from the wafer surface, so that any removal action caused by chemical (etching) attack on the wafer surface would be negligible or energetically disfavored. This however, has been discovered to not be the case. Contrariwise, the combination of SCF and fluoro species has been

demonstrated to be an effective cleaning combination having superior ability to remove polymer resist materials as well as post-ash residues from the wafer surface.

[0026] SCF/fluoro species compositions of the invention are readily formulated for use in cleaning of oxides and oxide-containing residues, by subjecting the source fluid for the SCF to pressure and temperature conditions above the critical point where the source fluid becomes a supercritical fluid. Once the source fluid is in the SCF state, the fluoro species and optional other ingredients of the composition are added, e.g., under simple mixing or blending conditions to produce a homogeneous cleaning composition.

[0027] Such optional other ingredients include co-solvent media (to enhance the solubility of the fluoro species in the SCF), inhibitors (to prevent or at least minimize attack of the cleaning composition on low k and other susceptible materials on the wafer surface), surfactants (to increase the homogeneity of the composition and the compatibility of its blended components), and other additives, adjuvants and enhancers such as may be useful or desirable in a given cleaning operation.

[0028] The SCF used in compositions of the invention can be of any suitable type. Non-limiting examples of SCF species that can be used in the broad practice of the invention include carbon dioxide, oxygen, argon, krypton, xenon, ammonia, methane, methanol, dimethyl ketone, hydrogen, forming gas, and sulfur hexafluoride. Carbon dioxide is particularly preferred.

[0029] Fluoro species usefully employed in the broad practice of the invention include, without limitation, hydrogen fluoride (HF), ammonium fluoride (NH_4F), alkyl hydrogen fluoride (NRH_3F), dialkylammonium hydrogen fluoride ($\text{NR}_2\text{H}_2\text{F}$), trialkylammonium hydrogen fluoride (NR_3HF), trialkylammonium trihydrogen fluoride ($\text{NR}_3(3\text{HF})$), tetraalkylammonium fluoride (NR_4F), and xenon difluoride (XeF_2), wherein each R in the aforementioned R-substituted species is independently selected from $\text{C}_1\text{-C}_8$ alkyl and $\text{C}_6\text{-C}_{10}$ aryl. Triethylamine trihydrogen fluoride is a preferred fluoro species due to its mild fluorination properties and favorable solubility in CO_2 when supercritical carbon dioxide SCCO_2 is employed as the SCF species. Ammonium fluoride is another preferred fluoro species, e.g., in compositions containing co-solvent media, due to its low toxicity and ease of

handling, as well as the acid-base buffering action associated with the ammonia-HF combination.

[0030] Co-solvent species useful in the cleaning compositions of the invention may be of any suitable type, including alcohols, amides, ketones, esters, etc. Illustrative species include, but are not limited to, methanol, ethanol, and higher alcohols, N-alkylpyrrolidones or N-arylpyrrolidones, such as N-methyl-, N-octyl-, or N-phenyl- pyrrolidones, dimethylsulfoxide, sulfolane, catechol, ethyl lactate, acetone, butyl carbitol, monoethanolamine, butyrol lactone, diglycol amine, γ -butyrolactone, butylene carbonate, ethylene carbonate, and propylene carbonate. Alcohols such as methanol, ethanol and isopropyl alcohol (IPA) are especially preferred.

[0031] Inhibitor additives may be used in the compositions of the invention to inhibit attack of the cleaning composition on low dielectric constant layers. Inhibitor species such as organic acids and/or inorganic acids are usefully employed for such purpose. Boric acid is a particularly preferred species.

[0032] The relative proportions of the above-described ingredients of the cleaning compositions of the invention can be widely varied to achieve a desired solvating and removal effect in application to photoresist and post-ashing residue removal from semiconductor wafers.

[0033] In general the SCF species comprises a substantial major fraction of the cleaning composition, typically constituting from about 75% by weight, based on the weight of the cleaning composition, to about 99.9% by weight, on the same cleaning composition weight basis. The fluoro species can be present in a suitable amount in relation to the SCF species, and amounts of from about 0.01% by weight to about 5% by weight, based on the weight of the cleaning composition, are usefully employed in specific embodiments of the invention. Low k material attack-inhibitors may optionally be present in an amount of up to about 5% by weight, based on the total weight of the composition. Co-solvent species may optionally be employed in the compositions of the invention, at concentrations of up to about 25% by weight, based on the total weight of the composition, when employed to increase solubility of the fluoro species in the particular SCF species employed. Surfactants may optionally be utilized in compositions

of the invention at concentrations of up to 5% by weight, based on the weight of the cleaning composition. In the compositions including such species, the total weight percent of all ingredients is 100%.

[0034] In a specific illustrative embodiment, the cleaning composition has the following formulation, wherein all percentages are by weight:

- a. Carbon dioxide: 80-99.01% (w/w)
- b. Fluoride species: 0.01-5.0% (w/w)
- c. Low-k material attack inhibitor: 0.0-5.0% (w/w)
- d. Co-solvent: 0-20% (w/w)
- e. TOTAL: 100% by weight

[0035] In another specific illustrative embodiment, the cleaning composition has the following formulation, wherein all percentages are by weight:

- a. Carbon dioxide: 80-99% (w/w)
- b. Fluoride species: 0.01-5.0% (w/w)
- c. Co-solvent: 1-20% (w/w)
- d. Surfactant: 0.0-5.0% (w/w)
- e. TOTAL: 100% by weight

[0036] The pressure of the cleaning composition can be in a range of from about 800 to about 10,000 psi, e.g., about 4000 psi, with temperature of the composition being in a range of from about 20 to about 150°C, and more preferably in a range of from about 40 to about 100°C, e.g., a temperature of about 50 to about 80°C.

[0037] In an illustrative cleaning process according to the present invention, in one embodiment thereof, the substrate (wafer) to be cleaned is placed in a sealed high-pressure chamber. The chamber then is filled with the cleaning composition of the invention, and the substrate is held under the cleaning solution for a predetermined time, at predetermined pressure and temperature, as appropriate to effect the desired cleaning of the substrate. The specific contact time of the cleaning composition with the substrate, and process (e.g.,

temperature and pressure) conditions can be readily determined by simple experiment, based on the disclosure herein, within the skill of the art.

[0038] After the substrate has been subjected to the cleaning composition for sufficient time and at sufficient processing conditions, the substrate may be rinsed with a solution containing only the SCF species, or alternatively containing only the SCF species and optional co-solvent(s), in order to remove the residue and the fluoro species. After rinsing for a sufficient time to effect appropriate removal of the residue and fluoro species, the cleaning chamber may be vented and the substrate may be removed. Appropriate rinsing conditions can readily be determined within the skill of the art, based on the disclosure herein, to achieve a specific removal character and extent.

[0039] In another aspect, the invention provides wafer cleaning compositions utilizing supercritical fluid (SCF) in combination with primary and/or secondary amine(s).

[0040] Such cleaning compositions, utilizing primary and/or secondary amine(s) in the SCF-based cleaning composition, optionally in combination with co-solvent(s), inhibitor(s) and/or surfactant(s), are advantageous for cleaning of photoresists, anti-reflective coatings, metal oxides and/or metal-containing residues that are present on the semiconductor wafer after plasma etching or ashing.

[0041] In such amine-containing SCF cleaning compositions, co-solvent(s) and/or surfactant(s) are optionally employed to enhance the compatibility of the primary and/or secondary amine(s) with the SCF in the composition. The composition can comprise from about 75% to about 99.9 % by weight, based on the weight of the cleaning composition, of the SCF, from about 0.01% to about 5.0% by weight of the primary and/or secondary amine(s), from about 0% to about 25% by weight of co-solvent(s), and up to about 5% by weight of surfactant(s), on the same total composition weight basis, with all ingredients of the composition totaling to 100 weight %. Compositions of such type may further optionally comprise inhibitor species to suppress attack on low k materials that may be present on the wafer being cleaned.

[0042] Particularly preferred amine-containing SCF cleaning compositions of above-described type include from about 80 to about 99.9% by weight of SCCO_2 , from about 0.01% to about 5.0% by weight of primary or secondary amine, from about 0% to about 20% by weight of co-solvent, and up to 5% by weight of surfactant, with all ingredient weight percentages being based on the total weight of the composition, and with all weight percentage amounts of such ingredients totaling to 100 weight %.

[0043] The SCF in such composition can suitably include any of the illustrative SCF species described hereinabove. SCCO_2 is a particularly preferred SCF species for such purpose. Suitable amines include, without limitation, hydroxylamine (NH_2OH), ammonia (NH_3), alkylamines (R-NH_2) and dialkylamines ($\text{R}_1\text{R}_2\text{NH}$), wherein R, R_1 and R_2 are each independently selected from C_1 - C_8 alkyl and C_6 - C_{10} aryl. Co-solvents can be of any suitable type, including alcohols, amides, ketones, esters, lactones, 1,3-diones, etc., with alcohols such as isopropyl alcohol (IPA) being particularly preferred. Surfactants likewise can be of any suitable type, preferably including a non-ionic surfactant such as the non-ionic surfactants commercially available from Air Products & Chemicals, Inc. under the trademark Surfynol®. Inhibitor(s), when used, can be of a type as previously described in connection with fluoro species-containing SCF cleaning compositions of the invention.

[0044] Amine-containing SCF cleaning compositions of the invention can be deployed for cleaning at any appropriate supercritical fluid conditions of temperature and pressure. Typically, such compositions are utilized at pressure in a range of from about 800 and about 10,000 psi, e.g., about 4000 psi, and temperature in a range of from about 20 to about 150°C, e.g., and more preferably from about 40 to about 100°C. Specific process conditions of temperature and pressure are readily determinable within the skill of the art based on the disclosure herein, by simple formulation, varying of process conditions, and determination of the nature and extent of cleaning thereby achieved, in a particular application of the cleaning composition.

[0045] The features and advantages of the invention are more fully illustrated by the following non-limiting examples.

[0046] FIG. 1 is a scanning electron microscope (SEM) micrograph of a post-ashing trench structure in a two-layer coating on a silicon substrate, wherein the two-layer coating includes a first (lower) layer of low k dielectric material and a second (upper) layer of a capping dielectric material, before cleaning.

[0047] FIG. 2 is an SEM micrograph of the trench structure of FIG. 1, after washing with a cleaning composition in accordance with one embodiment of the present invention. In FIG. 1, the post-ashing residue is visible as a continuous wall covering the trench sidewall. FIG. 2 shows the same trench structure after cleaning for approximately 2 minutes with a composition comprising a mixture of about 10% by weight ethanol solution in SCCO_2 , wherein the ethanol solution comprises about 0.5 wt % $(\text{C}_2\text{H}_5)_3\text{N}(3\text{HF})$ and about 0.25 weight % boric acid. A rinsing step follows after the cleaning step where the trench structure is rinsed in SCCO_2 solvent for approximately 5 minutes. Advantageously, the post-ashing (oxidizing or reducing) sidewall residue has been removed, without attack on the dielectric materials of the structure. Process conditions utilized in such embodiment include pressure, temperature and flow rate of approximately 4000 psi, 50°C and 50 mL/min., respectively.

[0048] FIGS. 3A and 3B are scanning electron microscope (SEM) micrographs of a post-ashing trench structure in a two-layer coating on a silicon substrate, wherein the two-layer coating includes a first (lower) layer of low k dielectric material and a second (upper) layer of a capping dielectric material, before cleaning.

[0049] FIG. 4 is an SEM micrograph of the trench structure in the two-layer coating on the silicon substrate of FIGS. 3A and 3B, after washing with a cleaning composition in accordance with a further embodiment of the present invention. FIG. 4 shows the same trench structure after cleaning for approximately 2 minutes with a composition comprising a mixture of about 10% by weight isopropanol solution in SCCO_2 , wherein the isopropanol solution comprises about 0.5 wt % NHF_4 , about 0.25 wt % boric acid, and 0.5 wt % surfactant. A rinsing step follows after the cleaning step where the trench structure is rinsed in SCCO_2 solvent for approximately 5 minutes. Process conditions utilized in such embodiment include pressure, temperature and flow rate of approximately 4000 psi, 50°C and 50 mL/min., respectively.

[0050] Post-ash residue is clearly visible on the surface of the wafer in FIGS. 3A and 3B. FIG. 4 shows that after cleaning the post-ash residue has been removed, with some etching of the dielectric materials. An undercut is visible, which is due to faster etching of the lower (low k) dielectric material.

[0051] The micrographs of FIGS. 1-4 thus evidence the efficacy of the cleaning compositions of the invention, for high efficiency cleaning of post-ashing residue on semiconductor wafers.

[0052] While the invention has been described herein in reference to specific aspects, features and illustrative embodiments of the invention, it will be appreciated that the utility of the invention is not thus limited, but rather extends to and encompasses numerous other aspects, features and embodiments. Accordingly, the claims hereafter set forth are intended to be correspondingly broadly construed, as including all such aspects, features and embodiments, within their spirit and scope.